

U30S DATA SHEET

FIBER PROPERTIES

Fiber	Result	Test method
Tensile Strength	5300MPa/ 770Ksi	ASTM D3039
Tensile Modulus	295GPa/ 42.8Msi	ASTM D3039
Stain	1.8%	ASTM D3039
Density	1.8 g/cm ³	ASTM D3800
Filament Diameter	7 μm	
Yield (12K/ 24K)	760g/1000m; 1520g/1000m	
Sizing Type	Epoxy	
Sizing Amount	1.2%	

PACKING

The table below summarizes the standard packaging.

Tow size	Bobbin net weight (kg)	Spools per case	Case net weight (kg)
12K/24K	3.9	6	23.4
12K	2	6	12

STORAGE

The recommended storage of the product temperature is between 20-30°C (68°F-86°F), the humidity is between 60-70%, and it can be stored for 24 months.

UHT Unitech Co., Ltd.

<http://www.uht.com.tw/>

sherry_lin@uht.com.tw

TEL: +886-3-435-6618 FAX: +886-3-435-6616

Address: No.8-2, Dingning Rd., Zhongli City, Taoyuan County 320, Taiwan